

Product technical specification

To protect the privacy of customers or suppliers of Salamander Jewelry. We erased their address from this document.

BRASS FOR CASTING

Pag. 1/1

Chemical specification

Main composition

<i>Elements</i>	<i>Unit</i>	<i>Value</i>	<i>Reference value</i>	<i>Analysis method</i>
Zn	%	11.9 - 13.9	12.9	I.C.P.
Si	%	2.9 - 3.3	3.1	I.C.P.
Cu + other elements	%	balance	balance	I.C.P.
Mn	%	0.8 - 1.3	1.0	I.C.P.

Impurities

<i>Elements</i>	<i>Value</i>	<i>Elements</i>	<i>Value</i>	<i>Elements</i>	<i>Value</i>	<i>Elements</i>	<i>Value</i>
Al	< 20 ppm	Co	< ppm	P	< ppm	Sn	< ppm
As	< 40 ppm	Cr	< 20 ppm	Pb	< 50 ppm	Sr	< ppm
Bi	< 25 ppm	Fe	< 250 ppm	S	< ppm	Te	< ppm
C	< ppm	Ni	< ppm	Sb	< 30 ppm	Tl	< ppm
Cd	< 10 ppm	O	< ppm	Si	< ppm	Totale	< 500 ppm
						Total	

Physical specification

- Grain size: smooth spheroidal grains with average diameter from 2 to 10 mm.
- Colour: yellow.

Packaging specification

Rolled polypropylene sacks of 10 Kg each. Tolerance: $\pm 0.10\%$ (± 10 g).

To protect the privacy of customers or suppliers of Salamander Jewelry. We erased their address from this document.

Other specifications

Further informations about our products are available on the Legor's Quality Statement Chart.

Revised

2

Issued

28/10/2015

To protect the privacy of customers or suppliers of Salamander Jewelry. We erased their address from this document.