

TEST REPORT




NO: RD-XR-103653

Date: Apr 05, 2016

Sample submitted:

Sample name: SNS13-E
Quantity of sample: 5 Pcs
Sample describe: SILVER JEWELED NIPPLE STIRRUP

Date information submitted: Apr 04, 2015



Conclusion:

<u>Tested sample:</u> Sample submitted	<u>Client's requirement:</u> Silver content	<u>Result:</u> Pass
---	--	------------------------

Test conducted:

1. Total Silver (Ag) content:

As In-house method based on USEPA 3052, acid digestion method was used and total Silver content was determined by Inductively Couple Plasma Optical Emission Spectrometry.

<u>Tested sample:</u> Sample submitted	<u>Result in %:</u> 96.74	<u>Client's requirement in %:</u> ≥ 92.50
Remark:	≥ = Rather than and equal > = Rather than < = Less than % = Percentage based on weight of sample	

Analyzed by:

HTek Edxrf Spectrometor medel No. 6000E
Sample type: Solid, Powder, Liquid
Tube voltage: 5 - 50 kV
Tube current: 0 - 100 uA
Test time: 30 - 100 Sec
Software: Htek-FP
Elements of interests Au, AG, PT, Pd, Ru, Rh, W, OS, IR, etc.
Basic metals Cr, Mn, Fe, Co, Ni, Cu, Zn, CD, Sn, Pb, etc.



Authorized by:
Salamander Jewelry Co., Ltd.

(*Jutha Liam*)

Mr. Jutha Liamukda
Research and Development Engineer
Sustainable Development Department